

# Cemimax DL33 Flex Fiber-Reinforced Smoothing Compound

## BPIR Declaration

Version: V1

---

### Designated building product: Class 1

---

### Declaration

Cemimax New Zealand Limited has provided this declaration to satisfy the provisions of Schedule 1(d) of the Building (Building Product Information Requirements) Regulations 2022.

---

### Product/system

<b>Name</b>	Cemimax DL33 Flex Fiber-Reinforced Smoothing Compound
<b>Line</b>	Fiber-Reinforced cementitious self-leveling smoothing compound for thickness from 1.5 to 100 mm
<b>Identifier</b>	

---

### Description

DL33 Flex is a Fiber-Reinforced cementitious self-leveling smoothing compound with enhanced flexural strength. It resists cracking and provides an exceptionally smooth, hard surface for use on timber substrate in residential and commercial areas.

## Scope of use

- DL33 Flex is formulated for leveling work on standard construction in level large commercial and retail areas.
- DL33 Flex is very suitable for normal traffic, quick-setting and economical surface preparation solutions.
- DL33 Flex can be applied from 1.5mm to 100mm thickness in one application.
- Suitable for radiant floor heating systems.
- Suitable for over acoustic underlays.
- Pigments can be added for color.
- Aggregates can be added for exposed stone effect.

---

## Conditions of use

### Substrate Preparation:

- The substrate must be sound, free from cracks, dry, clean and free from materials which would impair adhesion.
- Test the substrate according to applicable standards and report any deficiencies.
- Brush, abrade, grind or shot blast any weak surface sections or areas which will not accept adhesion.
- Thoroughly vacuum to remove loose material and dust.
- According to type and condition of the subfloor, apply suitable primer.
- Allow primers to dry thoroughly.

## Application:

- Put 4.4 - 4.8 liters of cold clean water into a clean container.
- Sprinkle in the sack contents (20kg) whilst stirring briskly and mix to a thick fluid. Lump-free consistency. Use a drill or mixer fitted with a Mixing Paddle. Do not mix too thinly.
- Pour the mixture on the area to be applied, spread the material uniformly to Required thickness using toothed rake. It is the next step to remove entranced air by particular roller.
- Drying time at 20°C is approx. 24 hours. Abrading using 40-60 grit sanding paper improves both the surface quality and the absorbency. Poor airflow and lower temperatures will significantly affect drying times.

---

## Contributions to compliance

B2.3.1(b) (ii) Cemimax DL33 Flex has durability of at least 15 years. F2.3.1 Cemimax DL33 Flex is safe when handled correctly as per Application Instructions on TDS.

---

## Contact details

<b>Manufacture location</b>	Overseas
<b>Legal and trading name of manufacturer</b>	Cemimax Australia Pty Ltd
<b>Legal and trading name of importer</b>	Cemimax New Zealand Limited
<b>Importer address for service</b>	23A Canaveral Drive, Rosedale Auckland 0632
<b>Importer website</b>	

Importer NZBN	9429051766979
Importer email	info@cemimax.co.nz
Importer phone number	02102313450

---

## Responsible person

As the responsible person as set out in Regulation 3, I confirm that the information supplied in this declaration is based on information supplied to the company as well as the company's own processes and is therefore to the best of my knowledge, correct.

I can also confirm that Cemimax DL33 Flex Fiber-Reinforced Smoothing Compound is not subject to a warning on ban under [s26 of the Building Act](#).

Signed for and on behalf of **Cemimax New Zealand Limited**:



Jeff Xu  
Director



June 2026

---

**CEMIMAX NEW ZEALAND LIMITED**

23A Canaveral Drive, Rosedale Auckland 0632 New Zealand

02102313450 | [info@cemimax.co.nz](mailto:info@cemimax.co.nz)